



SAC 0307 Lead-Free Solder

Physical Properties

Melting Temp (°F)	442
Melting Temp (°C)	227
Density (lbs/in ³)	0.265
Specific Gravity (g/m ³)	7.33
Hardness (HV)	14.1
Specific Heat Capacity (J/Kg)	0.17
Reflow Soldering Temp (°F)	455-473
Wave Soldering Pot Temp (°F)	491-509

Chemical Specifications

ELEMENT	JSTD-006C (%)
Tin (Sn)	98.5 - 99.5
Silver (Ag)	0.2 - 0.4
Cadmium (Cd)	0.002
Lead (Pb)	0.07
Aluminum (Al)	0.005
Copper (Cu)	0.60 - 0.80
Arsenic (As)	0.03
Iron (Fe)	0.02
Zinc (Zn)	0.003
Gold (Au)	0.05
Indium (In)	0.10
Antimony (Sb)	0.20
Bismuth (Bi)	0.10
Nickel (Ni)	0.001

Additional solder alloys manufactured by Nathan Trotter

Lead-Free Alloys

Sn96.5/Ag3.0Cu0.5 (SAC 0305)
Sn100 (Tin Bar)
Sn95/Sb5
Sn97/3Cu

Leaded Alloys

Sn60/Pb40
Sn62/Pb36/Ag2
Sn30/Pb70
Sn20/Pb80
Sn40/Pb60
Sn63/Pb 37—(SN63)

Limits are % max unless otherwise shown as range or stated otherwise. Except where otherwise indicated, the component elements in each alloy shall deviate from their nominal mass percentage by not > 0.10% of the alloy mass when their nominal percentage is ≤ 1.0%; by not > 0.20% of the alloy mass when their nominal percentage is > 1.0% to ≤ 5.0% or by not > 0.50% when their nominal percentage is > 5.0%.

Main Office

Nathan Trotter & Co., Inc.
241 W. Stewart Huston Dr.
Coatesville, PA 19320

Mailing Address

P.O.Box 369
Sadsburyville, PA 19369

P 610.524.1440

F 610.524.2469

info@nathantrotter.com

www.nathantrotter.com

Quality Metals Since 1789

ISO Certified Since 1997 / Tin / Tin Alloys / Solder / Nonferrous Metals



APPLICATION

Nathan Trotter solder bar performs favorably in wave soldering, solder dip, and solder coating applications. For solder plating applications, please refer to Nathan Trotter ANODES.

BAR SIZE/SHAPE

Standard sizes typically vary by application.

Application	Bar Description	Approx. Weight
Wave (PCB/THT)	KG Bar, Tri-Bar, Feeder Bar	1 lb, 2.2 lbs, 20 lbs

PACKAGING

Packaging can be made to customer specification. Standard packaging is either boxed (25 lbs or 50 lb boxes) or in the case of larger ingots, stacked and wrapped on a pallet. Each box is labeled with the alloy name, lot number, date of manufacture, weight of packaging unit, and any customer specific information required. Each lot will be accompanied by a certificate of analysis showing lot-specific chemistry.

POT MAINTENANCE

In conjunction with the use of Nathan Trotter solder bar, NT offers a complimentary solder pot analysis program to ensure the user's application remains at optimal chemistry. In-house OES spectrometers are used for a timely turnaround for customer samples. It is recommended that this program is utilized regularly to verify pot chemistry is within operating specification.

RECYCLING / RECLAIM

Tin Technology and Refining (www.tintech.com) is the recycling/reclaim division of Nathan Trotter. Tin Tech works in conjunction with Nathan Trotter solder bar customers to recycle dross, drippings, residues, paste, and other solder scrap that is generated from the use of solder. Tin Tech operates as a permitted, environmentally responsible smelter with full reduction capabilities enabling optimal recoveries for all types of solder scrap material.

STORAGE, HANDLING, SHELF LIFE

Nathan Trotter Solder Bar has an indefinite shelf life when stored in a dry, non-corrosive environment. Bars and packages should always be handled with care as material is naturally heavy.

HEALTH AND SAFETY

This product, during handling or use, may be hazardous to your health. Read the Safety Data Sheet (SDS) and warning label prior to use. SDS can be downloaded from our home page www.nathantrrotter.com

**For Sales or Technical Assistance, contact Nathan Trotter & Co:
Info@nathantrrotter.com or 610-524-1440**